


# rLLDPE



## APPLICATION



Plastic bags



Shrink film



PE sheets



Bubble Wrap

### Product Description

A1 - Recycled LLDPE  
(natural) pellets

### Sources

Recovered from  
post consumer  
LDPE stretch films

### Manufactory

Indonesia

## Property

Melt Flow(g/10 mins+2.16kg/190C)  
Specific Gravity  
Tensil Strength at Yield  
Elongation at Yield  
Ash Content @ 600C, 3h  
Filter Mesh Size

ASTM-D1238  
ASTM-D792  
ASTM-D638  
ASTM-D638  
Internal

## Nominal Values

2g/10 minutes  
0.96g/cm<sup>3</sup>  
15.1 mpa  
1500%  
<0.1%  
105um filter mesh

Disclaimer: This information is offered solely as a guide for your consideration and investigation. The values quoted are based on tests conducted on representative samples and are indicative only. It is not to be construed as a warranty or representation for which Horizons Resources Ltd assumes legal liability, except to the extent that such liability is imposed by legislation and cannot be excluded.



Horizons Resources Ltd  
Unit 7 Epic Park, Halesfield 6  
Telford, TF7 4BF  
United Kingdom



+44 (0) 1952 585 855



info@horizonsresources.com



www.horizonsresources.com