

rLDPE



APPLICATION



Plastic bags



Shrink film



PE sheets



Bubble Wrap

Product Description

A2 - Recycled LDPE natural pellets

Sources

Post consumer LDPE films

Manufactory

Indonesia

Property

Melt Flow(g/10 mins+2.16kg/190C)
Specific Gravity
Tensil Strength at Yield
Elongation at Yield
Ash Content @ 600C, 3h
Filter Mesh Size

ASTM-D1238
ASTM-D792
ASTM-D638
ASTM-D638
Internal

Nominal Values

0.4g/10 minutes
0.95g/cm³
13 mpa
986%
0.6%
105umfilter mesh

Disclaimer: This information is offered solely as a guide for your consideration and investigation. The values quoted are based on tests conducted on representative samples and are indicative only. It is not to be construed as a warranty or representation for which Horizons Resources Ltd assumes legal liability, except to the extent that such liability is imposed by legislation and cannot be excluded.



Horizons Resources Ltd
Unit 7 Epic Park, Halesfield 6
Telford, TF7 4BF
United Kingdom



+44 (0) 1952 585 855



info@horizonsresources.com



www.horizonsresources.com