

## rHDPE



## **APPLICATION**











**Pipes** 

Packaging film

**Pallets** 

Fuel tanks

**Containers** 

**Product Description** 

**B2 - Recycled HDPE** Pellets - Grey

Sources

Post consumer HDPE jazz bottles

Manufactory

Indonesia

## **Property**

Melt Flow (g/10 mins +2.16kg/190C) **Specific Gravity** Tensil Strength at Yield **Elongation at Yield** Ash Content @ 600C, 3h

**ASTM-D1238** ASTM-D792 ASTM-D638 ASTM-D638 Internal

## **Nominal Values**

0.4g/10 minutes 0.96g/ cm<sup>3</sup> 22.30 mpa 930.5% 1.15%

Disclaimer: This information is offered solely as a guide for your consideration and investigation. The values quoted are based on tests conducted on representative samples and are indicative only. It is not to be construed as a warranty or representation for which Horizons Resources Ltd assumes legal liability, except to the extent that such liability is imposed by legislation and cannot be excluded.







